

## ER2001 Epoxy Resin

ER2001 is a flame retardant, general purpose, two part potting and encapsulating compound. The flame retardant technology used is of a 'clean' type leading to relatively low toxicity fumes and low smoke emission.

- General purpose resin with long pot life; cost effective protection
- UL approved; UL94 V-0 flame retardancy rating
- Excellent electrical properties; offers protection in a wide range of conditions
- Easy to mix; colour differences of resin and hardener allow visual checking for efficient mixing

<b>Approvals</b>	<b>RoHS Compliant (2015/863/EU):</b>	<b>Yes</b>
	<b>UL Approval:</b>	<b>UL94 V-0 (File: E100107)</b>

### Typical Properties


Liquid Properties:	Base Material	Epoxy
	Density Part A - Resin (g/ml)	1.82
	Density Part B - Hardener (g/ml)	0.93
	Part A Viscosity (mPa s @ 23°C)	150000
	Part B Viscosity (mPa s @ 23°C)	25
	Mixed System Viscosity (mPa s @ 23°C)	9000
	Mix Ratio (Weight)	17.45:1
	Mix Ratio (Volume)	8.94:1
	Usable Life (20°C)	150 mins
	Gel Time (23°C)	5 hours
	Cure Time (23°C)	24 hours
	Cure Time (60°C)	4 hours
	Cure Time (100°C)	30 mins
	Colour Part A - Resin	Off-White
	Colour Part B - Hardener	Black
	Storage Conditions	Dry Conditions: Above 15°C, Below 30°C
	Shelf Life	24 Months (bulk) 18 months (resin pack)
	Exotherm	< 35°C
	(Measured on 100ml sample in a cylinder of diameter 49.4mm @ 23°C)	
	Shrinkage	< 0.5%

Cured System:	Thermal Conductivity (W/m.K)	0.55
	Cured Density (g/ml)	1.73
	Temperature Range (°C)	-40 to +130
	Max Temperature Range (Short Term (°C)/30 Mins) (Application and Geometry Dependent)	+150
	Dielectric Strength (kV/mm)	10
	Volume Resistivity (ohm-cm)	10 <sup>15</sup>
	Shore Hardness	D85
	Colour (Mixed System)	Black
	Flame Retardancy	Yes
	Tensile Strength (MPa)	50
	Compressive Strength (MPa)	120
	Deflection Temperature (°C)	60
	Coefficient of Expansion (ppm/°C)	35
	Loss Tangent @ 50 Hz	0.04
	Permittivity @ 50 Hz	5.00
	Comparative Tracking Index	>850 Volts
	Water Absorption (9.7mm thick disk, 51mm diameter) 10 days @ 20°C / 1 hour @ 100°C	< 0.5% / < 1%
	Elongation At Break	0.4%

## **Mixing Procedures**

### **Resin Packs**

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from two to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser.



**Bulk Mixing**

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing will result in erratic or partial curing.

**General**

Sedimentation of the resin has been minimised by careful attention to the formulation. However, any sediment which may have occurred over long periods of time must be dispersed before removing any material from the container. This dispersion can be carried out (if necessary) by stirring with a broad bladed spatula or gently rolling the can. Take care not to introduce excessive amounts of air during this operation or it may be necessary to re-evacuate the resin. Sedimentation will be accelerated by storage at high temperatures. Sedimentation found in resin packs forms no problem since the sediment is re-mixed when the pack is used.

**Additional Information**

- Cleaning:** It is far easier for machines & containers to be cleaned before the resin has been allowed to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured resin may be slowly softened and removed by soaking in our RRS.
- Curing:** Do not heat cure large volumes immediately. Allow these to gel at room temperature and post-cure at high temperature if required (refer to liquid properties for details). Small volumes (250ml) may be heat cured immediately.
- Storage:** When storing under very cold conditions, the hardener may crystallise. If this occurs, simply warm (40°C) the container gently until all crystals have re-melted.
- Health & Safety:** Always refer to the Health & Safety data sheet before use. These can be downloaded from [www.electrolube.com](http://www.electrolube.com)

Revision 2: Jan 2019