



Shallin Electronics Co., Ltd.

Item No.	SL7060			
			98.11.02	Unit
				mm

Technical Information: SL7060-72

	Properties		Unit	Test Method
Physical	Color	Gray	Visual	--
	Reinforcement Layer	Fiberglass	--	--
	Finish	Smooth	Visual	--
	Thickness (Tol. ± 0.02)	0.23~0.8	mm	ASTM D374
	Operating Temperature	-40~+220	$^{\circ}\text{C}$	--
Mechanical	Specific Gravity	1.60	g/cm^3	ASTM D792
	Tensile Strength	150	kgf/cm^2	ASTM D412
	Tear Strength	6.70	kgf/cm	ASTM D642
	Elongation	7~12	%	ASTM D412
	Hardness	70 ± 5	Shore A	ASTM D2240
Electrical	Voltage Breakdown	3.5	kV	ASTM D149
	Volume Resistivity	2.0×10^{13}	$\Omega \cdot \text{cm}$	ASTM D257
Thermal	Thermal Conductivity	0.3	$\text{W}/\text{m.k}$	ASTM D5470
Regulatory	Flammability Rating	V-0	--	UL 94
	RoHS Compliant	Yes	--	Lab. Certification
	PFOA Compliant	Yes	--	Lab. Certification
	PFOS Compliant	Yes	--	Lab. Certification
	SVHC Compliant	Yes	--	Lab. Certification

* The above testing results comes from laboratory report, information are for your reference only.